

# Articles

## A Study on the Structure and Thermal Property of $\text{Cu}^{2+}$ and $\text{NH}_4^+$ Ion-Exchanged Zeolite A

Jong-Yul Park\*, Mi-Sook Kang, Sang-Gu Choi†, Yang Kim, and Un-Sik Kim

Department of Chemistry, Pusan National University, Pusan 609-735

†Yong San Junior College, Yang San 626-825. Received September 18, 1992

The frameworks of  $(\text{Cu}(\text{NH}_3)_3\text{OH}^+)_x(\text{NH}_4^+)_{12-x}\text{-A}\cdot z\text{H}_2\text{O}$  which were prepared by the ion-exchange of zeolite A with ammoniac cupric nitrate solution are more stable than those of  $\text{Cu}_x\text{Na}_{12-2x}\text{-A}$  obtained by the ion exchange with aqueous cupric nitrate solution. An energetic calculation was made on the relatively stable  $(\text{CuOH}^+)_2(\text{NH}_4^+)_{10}\text{-A}\cdot 2\text{H}_2\text{O}$  prepared by the partial evacuation of  $(\text{Cu}(\text{NH}_3)_3\text{OH}^+)_2(\text{NH}_4^+)_{10}\text{-A}\cdot z\text{H}_2\text{O}$ . The mean stabilization energies of water,  $\text{OH}^-$ , and  $\text{NH}_4^+$  ions are  $-30.23$  kcal/mol,  $-60.24$  kcal/mol, and  $-16.65$  kcal/mol, respectively. The results of calculation were discussed in terms of framework stability. The  $(\text{Cu}(\text{NH}_3)_3\text{OH}^+)_2(\text{NH}_4^+)_{10}\text{-A}\cdot z\text{H}_2\text{O}$  zeolite shows two step deammoniation reactions. The first deammoniation around  $210^\circ\text{C}$  (third DSC peak) was attributed to the decomposition of  $[\text{Cu}(\text{NH}_3)_3\text{OH}]^+$  ion and the second one around  $380^\circ\text{C}$  (fourth DSC peak) was ascribed to the decomposition of  $\text{NH}_4^+$  ion. The activation energies of the first and second deammoniation reactions were  $99.75$  kJ/mol and  $176.57$  kJ/mol, respectively.

### Introduction

Zeolites are a class of aluminosilicates with relatively rigid anionic frameworks which have the well-defined channels and cavities,<sup>1</sup> and they contain exchangeable cations and removable guest molecules inside their framework.

They are used widely as catalysts, ion exchangers, and selective sorbing agents<sup>2</sup> due to their structural characteristics and unusual physicochemical properties.

The framework of zeolite A can be considered as a rigid polydentate ligand within which the exchangeable 12  $\text{Na}^+$  ions are located at suitable sites inside the framework. The structure of Zeolite A can be described in terms of a simple cubic arrangement of the sodalite unit ( $\beta$ -cage) enclosing a cavity with a free diameter of  $6.6 \text{ \AA}$ . The cubic D4R units ( $\text{Al}_4\text{Si}_4\text{O}_{16}$ ) are placed in the centers of edges of the cube ( $12.3 \text{ \AA}$ ) and are bridged with sodalite units. A large cavity ( $\alpha$ -cage) with a free diameter of  $11.4 \text{ \AA}$  is formed in the center of unit cell.

The most definite structural informations on the zeolites are obtained from single crystal X-ray diffraction and neutron diffraction. Infrared,<sup>3</sup> Raman,<sup>4</sup> EPR,<sup>5</sup> and solid NMR<sup>6</sup> spectroscopy are also useful means to study the zeolite structure.

Recently, many theoretical studies have been made to obtain the structural and energetic informations on the zeolite framework using some potential functions.<sup>7-9</sup> and molecular orbital method.<sup>10-12</sup>

It is generally believed that the nature of cations, such as their locations, coordination environments, and oxidation state are responsible for the profound effects on the physicochemical properties of zeolites.<sup>13</sup> Sometimes, the ion-exchange of zeolite is accompanied by dramatic alterations of stability, adsorption behavior, catalytic activity, and other physicochemical properties.

It has been reported that the structures of some cation-

exchanged zeolites are lost when they are evacuated at higher temperature due to their instability of their framework.<sup>14,15</sup>

In this work, the framework stability and deammoniation reaction of hydroxotriammineCu(II)- and  $\text{NH}_4^+$ -exchanged zeolite A,  $(\text{Cu}(\text{NH}_3)_3\text{OH}^+)_x(\text{NH}_4^+)_{12-x}\text{-A}\cdot z\text{H}_2\text{O}$ , will be examined by means of powder X-ray diffraction, FT-IR, and thermal analysis. At the same time, an energetic calculation will be made on the relatively stable  $(\text{CuOH}^+)_2(\text{NH}_4^+)_{10}\text{-A}\cdot 2\text{H}_2\text{O}$  prepared by the partial evacuation of  $(\text{Cu}(\text{NH}_3)_3\text{OH}^+)_x(\text{NH}_4^+)_{12-x}\text{-A}\cdot z\text{H}_2\text{O}$  (where  $x=2.0$ ), and the calculated structure and stabilization energies will be discussed in terms of the framework stability.

### Experimental

Since the extensive ion exchange of  $\text{Cu}^{2+}$  ion into zeolite A with aqueous cupric nitrate solution damage the zeolite structure, ammoniac cupric nitrate solution was used for ion exchange in this work.

The ion-exchange of zeolite A with ammoniac cupric nitrate solution which was prepared by adding  $5 \text{ ml}$  of  $16 \text{ M}$   $\text{NH}_4\text{OH}$  to  $95 \text{ ml}$  of  $0.1 \text{ M}$   $\text{Cu}(\text{NO}_3)_2$  solution yielded hydroxotriammineCu(II)- and  $\text{NH}_4^+$ -exchanged zeolite A,  $(\text{Cu}(\text{NH}_3)_3\text{OH}^+)_x(\text{NH}_4^+)_{12-x}\text{-A}\cdot z\text{H}_2\text{O}$  ( $x=0.85, 1.24, \text{ and } 2.00$ ). Further ion-exchange above  $x=2.0$  was not achieved with this ion-exchanging solution at room temperature.

Powder X-ray diffractograms within  $2^\circ < 2\theta < 50^\circ$  were recorded on the Rigagu Geigerflex D/Max diffractometer with Ni-filtered  $\text{CuK}\alpha$  radiation. All samples were scanned at the rate of  $2^\circ (2\theta)$  per minute under the condition of time constant=1, CPS/FS: 2000, the power:  $40 \text{ kV}$  and  $30 \text{ mA}$ .

The IR spectra in the region of  $400\text{-}2000 \text{ cm}^{-1}$  were obtained using Mattson-Polaris TM spectrometer.

The thermograms of differential scanning calorimeter

(DSC), thermogravimetric analysis (TGA), and differential thermal analysis (DTA) were recorded on a Rigagu Thermal Analyzer TAS 100 system at ambient.

### Calculation

#### Model Compound

The geometry of partially dehydrated  $(\text{CuOH}^+)_{2.0}(\text{NH}_4^+)_{10.0} \cdot \text{A} \cdot 2\text{H}_2\text{O}$  was taken from X-ray crystallographic study.<sup>3</sup>

#### Optimization

The positions and stabilization energies of  $\text{NH}_4^+$ ,  $\text{OH}^-$ , and water molecules inside partially dehydrated  $(\text{CuOH}^+)_{2.0}(\text{NH}_4^+)_{10.0} \cdot \text{A} \cdot 2\text{H}_2\text{O}$  were determined using some potential functions and optimization program.<sup>16</sup>

The total stabilization energy ( $V_{\text{tot}}$ ) is expressed as a sum of electrostatic energy ( $V_{\text{el}}$ ), polarization energy ( $V_{\text{pol}}$ ), dispersion energy ( $V_{\text{disp}}$ ), and repulsion energy ( $V_{\text{rep}}$ ).

$$V_{\text{tot}} = V_{\text{el}} + V_{\text{pol}} + V_{\text{disp}} + V_{\text{rep}}$$

**Electrostatic energy ( $V_{\text{el}}$ ).** The net charges of the atoms are considered as point charge. Electrostatic energy is given as

$$V_{\text{el}} = \sum_i \sum_j^{(1)(2)} (\delta_i \delta_j) / DR_{ij}$$

where  $\delta_i$  and  $\delta_j$  are the charges of the  $i$ th and  $j$ th atoms, respectively and  $R_{ij}$  is their interatomic distance. The dielectric constant  $D$  was determined by comparing the calculated average binding energy of water molecules with the dehydration enthalpy measured by DSC. The optimum value of dielectric constant in this work was 2.9.  $i$  and  $j$  represent framework atoms.

The net atomic charges are calculated using Hueey's electronegativity set and Sanderson's electronegativity equalization method. The calculated net atomic charges are:  $\delta_{\text{T1}} = 0.5861$ ,  $\delta_{\text{T2}} = 0.5861$ ,  $\delta_{\text{Na}} = 0.625$ ,  $\delta_{\text{O(1)}} = -0.4509$ ,  $\delta_{\text{O(2)}} = -0.4548$ ,  $\delta_{\text{O(3)}} = -0.4458$ ,  $\delta_{\text{Cu}} = 1.250$ .

**Polarization energy ( $V_{\text{pol}}$ ).** Polarization energy is given as follows:

$$V_{\text{pol}} = -1/2 \sum_i \alpha_i \left[ \left( \sum_{j \neq i}^{\rightarrow x} E_{ij} \right)^2 + \left( \sum_{j \neq i}^{\rightarrow y} E_{ij} \right)^2 + \left( \sum_{j \neq i}^{\rightarrow z} E_{ij} \right)^2 \right]$$

**Table 1.** The Coordinates of Framework Atoms and  $\text{Cu}^{2+}$  Ions in  $(\text{Cu}(\text{OH})^+)_{2.0}(\text{NH}_4^+)_{10.0} \cdot \text{A} \cdot 2\text{H}_2\text{O}^3$

| Framework atom | Coordinate |         |         |
|----------------|------------|---------|---------|
|                | $x$ (Å)    | $y$ (Å) | $z$ (Å) |
| T <sub>1</sub> | 1.5694     | 6.1400  | 3.8805  |
| O(3)           | 1.9230     | 7.5178  | 4.7622  |
| O(2)           | 2.5395     | 6.1400  | 0.0000  |
| T <sub>2</sub> | 3.8805     | 6.1400  | 1.5694  |
| O(3)'          | 4.7622     | 4.7622  | 1.9230  |
| O(1)           | 3.3795     | 6.1400  | 0.0000  |
| Cu(1)          | 3.8498     | 3.8498  | -3.8498 |
| Cu(2)          | -3.8498    | -3.8498 | 3.8498  |

$$V_{\text{pol}(i,j)} = V_{\text{pol}(i \rightarrow j)} + V_{\text{pol}(j \rightarrow i)}$$

where  $\bar{\alpha}_i$  is the atomic polarizability of the  $i$ th atom and  $\bar{E}_j$  is the electric field created by  $j$ th atom at the position of  $i$ th atom in the  $x$ -direction

**Dispersion and repulsion energy ( $V_{\text{d,r}}$ ).** A modified Kitaigorodskii potential function<sup>17</sup> was used for the description of dispersion and repulsion between all  $i$  and  $j$  atom.

$$V_{\text{d,r}} = V_{\text{dis}} + V_{\text{rep}}$$

$$V_{\text{d,r}} = \sum_i \sum_{j>i} k_i k_j \left[ -A/Z^6 + (1 - \delta_i/N_i^{\text{val}}) (1 - \delta_j/N_j^{\text{val}}) C \exp(-\alpha R_{ij}/R_{ij}^{\text{v}}) \right]$$

where  $R_{ij}$  is an inter atomic distance,  $Z = R_{ij}/R_{ij}^{\text{v}}$  and  $R_{ij}^{\text{v}} = [(2R_i^{\text{v}})(2R_j^{\text{v}})]^{1/2}$  and  $R_i^{\text{v}}$ ,  $R_j^{\text{v}}$  are the van der Waals radii of atom  $i$  and  $j$ . The parameter  $A$ ,  $C$ , and  $\alpha$  are 0.214 kcal/mol, 47,000 kcal/mol, and 12.35 respectively.

The multiplication factor  $k_i$  and  $k_j$  represents the nature of the interacting atom  $i$  and  $j$ . The values used in this work are  $k_{\text{H}} = 1.00$ ,  $k_{\text{O}} = 1.36$ ,  $k_{\text{T}} = 2.10$ ,  $k_{\text{Na}} = 2.86$ ,  $k_{\text{Cu(II)}} = 3.00$ .  $\delta_i$  is the net charge of atom  $i$ , and  $N_i^{\text{val}}$  is the number of valence electrons of neutral atom  $i$ . This modified function was also applied to the case of hydrogen bond.


Table 1 shows the coordinates of framework atoms and  $\text{Cu}^{2+}$  ions in partially dehydrated  $(\text{Cu}(\text{OH})^+)_{2.0}(\text{NH}_4^+)_{10.0} \cdot \text{A} \cdot 2\text{H}_2\text{O}$ . The optimized positions and stabilization energies of water

**Table 2.** The Optimized Positions and Stabilization Energies of  $\text{OH}^-$  Ions and Water Molecules in  $(\text{CuOH}^+)_{2.0}(\text{NH}_4^+)_{10.0} \cdot \text{A} \cdot 2\text{H}_2\text{O}$  in parenthesis; crystallographic data<sup>3</sup>

| Group | Atom | Coordinate       |                  |                  | Stabilization energy (kcal/mol) |
|-------|------|------------------|------------------|------------------|---------------------------------|
|       |      | $x$ (Å)          | $y$ (Å)          | $z$ (Å)          |                                 |
| w(1)  | H    | 2.6628           | 2.8481           | -1.7454          | -29.716                         |
|       | O    | 2.6828(2.6844)   | 2.6824(2.6844)   | -2.6880(-2.6844) |                                 |
|       | H    | 1.7849           | 2.4317           | -2.9056          |                                 |
| w(2)  | H    | -2.6997          | -2.5383          | 1.7391           | -30.747                         |
|       | O    | -2.6851(-2.6844) | -2.6829(-2.6844) | 2.6853(2.6844)   |                                 |
|       | H    | -1.8376          | -3.0960          | 2.8517           |                                 |
| OH(1) | O    | 5.0907(5.0937)   | 5.0899(5.0937)   | -5.1005(-5.0937) | -63.857                         |
|       | H    | 5.4187           | 5.8345           | -5.6047          |                                 |
| OH(2) | O    | -5.0950(-5.0950) | -5.0908(-5.0950) | 5.0953(5.0950)   | -58.626                         |
|       | H    | -5.5955          | -5.0908          | 5.7906           |                                 |

**Table 3.** The Optimized Positions and Stabilization Energies of  $\text{NH}_4^+$  Ions in  $(\text{CuOH}^+)_2(\text{NH}_4^+)_{10}\text{-A}\cdot 2\text{H}_2\text{O}$ . in Parenthesis; Crystallographic Data<sup>3</sup>

| Group                     | Atom | Coordinate       |                  |                  | Stabilization energy (kcal/mol) |
|---------------------------|------|------------------|------------------|------------------|---------------------------------|
|                           |      | $x$ (Å)          | $y$ (Å)          | $z$ (Å)          |                                 |
| $\text{NH}_4(\text{I})$   | N    | 3.0842(3.0860)   | 3.0874(3.0864)   | 3.0864(3.0860)   | -16.378                         |
|                           | H    | 2.9878           | 4.0063           | 2.6787           |                                 |
|                           | H    | 2.3813           | 2.9599           | 3.8004           |                                 |
|                           | H    | 4.0021           | 2.9965           | 3.4980           |                                 |
|                           | H    | 2.9656           | 2.3867           | 2.3687           |                                 |
| /                         | N    | -3.0863(-3.0868) | -3.0879(-3.0860) | -3.0833(-3.0860) | -16.485                         |
|                           | H    | -3.1840          | -2.1673          | -3.4873          |                                 |
|                           | H    | -3.2063          | -3.7863          | -3.8031          |                                 |
|                           | H    | -3.7888          | -3.2176          | -2.3688          |                                 |
|                           | H    | -2.1681          | -3.1804          | -2.6740          |                                 |
| /                         | N    | -3.0868(-3.0860) | 3.0855(3.0860)   | 3.0851(3.0860)   | -16.801                         |
|                           | H    | -3.1814          | 4.0062           | 2.6796           |                                 |
|                           | H    | -3.7904          | 2.9579           | 3.7982           |                                 |
|                           | H    | -2.1694          | 2.9927           | 3.4971           |                                 |
|                           | H    | -3.2059          | 2.3874           | 2.3656           |                                 |
| /                         | N    | 3.0842(3.0866)   | -3.0855(-3.0860) | 3.0883(3.0860)   | -16.209                         |
|                           | H    | 3.0687           | -2.9528          | 2.0871           |                                 |
|                           | H    | 2.1391           | -3.0754          | 3.4444           |                                 |
|                           | H    | 3.6137           | -2.3406          | 3.5182           |                                 |
|                           | H    | 3.5153           | -3.9732          | 3.3033           |                                 |
| /                         | N    | 3.0842(3.0860)   | -3.0892(-3.0860) | -3.0846(-3.0860) | -18.247                         |
|                           | H    | 2.9853           | -2.1694          | -3.4901          |                                 |
|                           | H    | 2.9653           | -3.7890          | -3.8032          |                                 |
|                           | H    | 2.3829           | -3.2188          | -2.3694          |                                 |
|                           | H    | 4.0033           | -3.1796          | -2.6758          |                                 |
| /                         | N    | -3.0868(-3.0868) | 3.0824(3.0860)   | -3.0888(-3.0860) | -16.984                         |
|                           | H    | -3.1025          | 3.0824           | -2.0901          |                                 |
|                           | H    | -4.0138          | 3.8378           | -3.4077          |                                 |
|                           | H    | -2.4470          | 2.3318           | -3.3065          |                                 |
|                           | H    | -2.7842          | 3.9280           | -3.5509          |                                 |
| $\text{NH}_4(\text{II})$  | N    | 5.7504(5.7507)   | 0.4170(0.4175)   | -0.4180(-0.4175) | -16.361                         |
|                           | H    | 5.7506           | -0.5867          | -0.4178          |                                 |
|                           | H    | 6.9378           | 0.8016           | -0.1901          |                                 |
|                           | H    | 5.7112           | 0.6450           | 0.5653           |                                 |
|                           | H    | 4.9460           | 0.8082           | -0.8870          |                                 |
| /                         | N    | -0.4095(-0.4175) | 5.6506(5.7507)   | -0.4145(-0.4175) | -15.223                         |
|                           | H    | -0.4398          | 5.9903           | 0.5361           |                                 |
|                           | H    | -0.7001          | 4.6838           | -0.4365          |                                 |
|                           | H    | 0.5333           | 5.3726           | -0.7689          |                                 |
|                           | H    | -1.0306          | 6.2024           | -0.9889          |                                 |
| /                         | N    | -0.4167(-0.4175) | 0.4167(0.4175)   | 5.7505(5.7507)   | -16.548                         |
|                           | H    | -0.4669          | -0.0815          | 6.6276           |                                 |
|                           | H    | 0.5341           | 0.4049           | 5.4100           |                                 |
|                           | H    | -0.7126          | 1.3724           | 5.8890           |                                 |
|                           | H    | -1.0214          | -0.0290          | 5.0753           |                                 |
| $\text{NH}_4(\text{III})$ | N    | -4.7597(-4.7585) | 4.7530(4.7530)   | -4.7628(-4.7628) | -17.228                         |
|                           | H    | -4.7697          | 4.8481           | -3.7574          |                                 |
|                           | H    | -5.6970          | 4.5741           | -0.0938          |                                 |
|                           | H    | -4.1589          | 3.9836           | -5.0220          |                                 |
|                           | H    | -4.4133          | 5.6060           | -5.1781          |                                 |



**Figure 1.** The stereoview of the large cavity (a) and sodalite unit (b) of partially dehydrated  $(\text{CuOH}^+)_{2.0}(\text{NH}_4^+)_{10.0}\text{-A}\cdot 2\text{H}_2\text{O}$ .

molecules and  $\text{OH}^-$  ions are listed in Table 2, and those of  $\text{NH}_4^+$  ions are shown in Table 3, respectively.

Figure 1 shows the stereoview of the  $\alpha$ -cage and sodalite unit of partially dehydrated  $(\text{CuOH}^+)_{2.0}(\text{NH}_4^+)_{10.0}\text{-A}\cdot 2\text{H}_2\text{O}$  plotted using ORTEP program.<sup>18</sup>

## Results and Discussion

**Calculation.** The optimized positions and stabilization energies of  $\text{NH}_4^+$ ,  $\text{OH}^-$ , and water molecules inside the partially dehydrated  $(\text{CuOH}^+)_{2.0}(\text{NH}_4^+)_{10.0}\text{-A}\cdot 2\text{H}_2\text{O}$  were obtained using above potential energy functions and optimization program. The calculated positions of nitrogen atoms in  $\text{NH}_4^+$  and those of oxygen atoms in both  $\text{OH}^-$  and water molecules are agreed well with crystallographic data<sup>3</sup> (in parenthesis of Table 2 and 3).

This calculation show that  $\text{Cu}^{2+}$  ion lies on a three-fold axis, nearly in the O(3) plane of a 6-ring and this is coordinated equatorially with three O(3) framework oxygens and also axially with one  $\text{H}_2\text{O}$  and one  $\text{OH}^-$  ion in nearly trigonal bipyramidal manner. This agrees well with Herman's report.<sup>19</sup>

He observed that  $\text{Cu}^{2+}$  ions are coordinated octahedrally with framework oxygens and water molecules in hydrated state but upon evacuation, their coordinations are changed in trigonal bipyramidal manner having three coordinations with 6-ring oxygens and two coordinated water molecules axially.

The calculated bond angles of O(3)-Cu-O(4) and O(3)-Cu-O(5) are  $91^\circ$  and  $88.5^\circ$ , respectively. The distance between  $\text{Cu}^{2+}$  ion and oxygen atom O(5) of water molecule was 2.155 Å. The distance is good agreement with the single crystal X-ray diffraction data 2.150 Å.

The stabilization energies of w(1) and w(2) water molecules which are located in  $\alpha$ -cage near 6-ring along  $c_3$ -axis are

-29.716 kcal/mol and -30.747 kcal/mol, respectively.

The  $\text{OH}^-$  ions lie in the sodalite unit along  $c_3$ -axis and they are coordinated axially with  $\text{Cu}^{2+}$  ion more strongly than  $\text{H}_2\text{O}$ . The mean stabilization energy of  $\text{OH}^-$  ion is -61.242 kcal/mol. This large stabilization energy of  $\text{OH}^-$  ion will contribute to stabilize the framework of partially dehydrated  $(\text{CuOH}^+)_{2.0}(\text{NH}_4^+)_{10.0}\text{-A}\cdot 2\text{H}_2\text{O}$ .

The distance between  $\text{Cu}^{2+}$  and oxygen (O(4)) of  $\text{OH}^-$  is 2.019 Å and can be compared with crystallographic data (2.020 Å).

The nitrogen atoms of  $\text{NH}_4$ (I) group locating in large cavity are 2.64 Å apart from three O(3) framework oxygen atoms, and three hydrogen atoms of ammonium ion of this group are directed toward O(3) framework oxygen atoms to make hydrogen bonds. Three  $\text{NH}_4^+$  ions of  $\text{NH}_4$ (II) group lies at a site near the plane of 8-ring. The nitrogen atoms of this group are 3.02 Å apart from two O(1) and 3.03 Å apart from one O(2), respectively.

The similar locations of  $\text{NH}_4^+$  ions in partially dehydrated  $(\text{CuOH}^+)_{2.0}(\text{NH}_4^+)_{10.0}\text{-A}\cdot 2\text{H}_2\text{O}$  had been found in dehydrated  $(\text{NH}_4)_{12}\text{-A}$  zeolite.<sup>20</sup> The remaining one  $\text{NH}_4^+$  ion of  $\text{NH}_4$ (III) group is located in the sodalite unit opposite a 6-ring which was already associated with one  $\text{NH}_4^+$  ion of  $\text{NH}_4$ (II) group. The nitrogen atom of  $\text{NH}_4$ (III) group is 2.84 Å apart from three O(3) framework oxygen.

The order of mean stabilization energy of ammonium ions in each group is  $\text{NH}_4$ (III): -17.228 kcal/mol >  $\text{NH}_4$ (I): -16.851 kcal/mol >  $\text{NH}_4$ (II): -16.004 kcal/mol.

**Framework Stability.** Some of the cation-exchanged zeolite A, such as  $\text{K}^+$ ,  $\text{Mg}^{2+}$ ,  $\text{Ca}^{2+}$ , and  $\text{Sr}^{2+}$ -exchanged zeolite A are stable upon dehydration at higher temperature, but some others, such as  $\text{Ba}^{2+}$ ,  $\text{Fe}^{2+}$ , and  $\text{Ni}^{2+}$  ion-exchanged zeolite A are thermally unstable and their framework are almost collapsed by dehydration around 200°C.<sup>21</sup>


In this work, the X-ray diffraction and FT IR experiment show that the hydroxotriammineCu(II)- and  $\text{NH}_4^+$ -exchanged zeolite-A,  $(\text{Cu}(\text{NH}_3)_3\text{OH}^+)_x(\text{NH}_4^+)_{12-x}\text{-A}\cdot z\text{H}_2\text{O}$ , which were prepared by the ion exchange of zeolite A with ammoniac cupric nitrate solution are more stable than  $\text{Cu}_x\text{Na}_{12-2x}\text{-A}$  zeolites obtained by the ion-exchange with aqueous cupric nitrate solution.

All the samples of  $\text{Cu}^{2+}$  and  $\text{NH}_4^+$  ion-exchanged zeolite A show the similar X-ray diffraction patterns and intensities as those of thermally stable zeolite A ( $\text{Na}_{12}\text{-A}$ ) even after evacuation at 300°C for 5 hours (Figure 2). In spite of the same contents of  $\text{Cu}^{2+}$  ion,  $(\text{CuOH}^+)_{2.0}(\text{NH}_4^+)_{10.0}\text{-A}$  shows stronger XRD intensities than that of  $\text{Cu}_{2.0}\text{Na}_{8.0}\text{-A}$  prepared by the ion-exchange with aqueous cupric nitrate solution (Figure 2).

The IR spectroscopy also shows that the framework of  $(\text{Cu}(\text{NH}_3)_3\text{OH}^+)_x(\text{NH}_4^+)_{12-x}\text{-A}\cdot z\text{H}_2\text{O}$  are relatively stable (Figure 3). It is well known that the IR band at 550  $\text{cm}^{-1}$  due to external linkages, D4R, is sensitive to the zeolite structure.

The decrease in intensity and the broadening of this band indicates the disruption and decomposition of zeolite framework.

Figure 3 clearly shows that  $(\text{CuOH}^+)_x(\text{NH}_4^+)_{12-x}\text{-A}$  zeolites show the same IR absorption bands and intensities at 1000  $\text{cm}^{-1}$  (asymmetric stretching band of  $\text{TO}_4$ ), 550  $\text{cm}^{-1}$  (vibration of double 4-ring), and 670  $\text{cm}^{-1}$  (symmetric stretching vibration of  $\text{TO}_4$ ) as those in zeolite A after evacuation at




**Figure 2.** The X-ray diffractograms of  $\text{Cu}^{2+}$  and  $\text{NH}_4^+$  ion-exchanged zeolite A heated at  $300^\circ\text{C}$ . a:  $\text{Cu}_{2.0}\text{Na}_{8.0}\text{-A}$ , b:  $(\text{CuOH}^+)_{2.0}(\text{NH}_4^+)_{10.0}\text{-A}$ , c:  $(\text{CuOH})_{1.24}(\text{NH}_4^+)_{10.76}\text{-A}$ , d: zeolite A ( $\text{Na}_{12}\text{-A}$ ).

$300^\circ\text{C}$ . This indicates that the framework of  $(\text{Cu}(\text{NH}_3)_3\text{OH}^+)_x(\text{NH}_4^+)_{12-x}\text{-A}\cdot z\text{H}_2\text{O}$  are relatively stable.


Kim *et al.*<sup>14</sup> attributed the thermal instability of  $\text{Ba}^{2+}$  ion-exchanged zeolite A to the movement of large  $\text{Ba}^{2+}$  ion ( $1.34 \text{ \AA}$ ) from the position of hydrated state toward the small 6-ring site where large  $\text{Ba}^{2+}$  ion can not be accommodated well enough upon dehydration. N. H. Heo and K. Seff<sup>22</sup> ascribed the thermal instability of Ni(II)-exchanged zeolite A to the attack of protons to the framework oxygen atoms while the protons are accumulated inside framework by the hydrolysis of  $\text{Ni}^{2+}$  ions.

Since the ionic radius of  $\text{Cu}^{2+}$  ion ( $r_+ = 0.71 \text{ \AA}$ ) is quite smaller than  $\text{Ba}^{2+}$  ion ( $r_+ = 1.34 \text{ \AA}$ ), the size effect of  $\text{Cu}^{2+}$  ion on the framework instability can not be expected. However,  $\text{Cu}^{2+}$  ion has the same charge and similar ionic size as  $\text{Ni}^{2+}$  and  $\text{Fe}^{2+}$  ion and it may cause the hydrated water molecules to be hydrolyzed likewise  $\text{Fe}^{2+}$  and  $\text{Ni}^{2+}$  ion. In fact, the hydrolysis constant of Cu(II) ion ( $pK_{h(\text{Cu(II)})} \sim 10.36^{23}$ ) is comparable to those of  $\text{Fe}^{2+}$  and  $\text{Ni}^{2+}$  ( $pK_{h(\text{Ni(II)})} \sim 9.86^{22}$ ,  $pK_{h(\text{Fe(II)})} \sim 9.50^{23}$ ).

It is well known that zeolite structure are damaged in acidic solution due to the attacking of proton to framework



**Figure 3.** The infrared spectra of  $(\text{CuOH}^+)_x(\text{NH}_4^+)_{12-x}\text{-A}$  zeolite heated at  $300^\circ\text{C}$ . a:  $(\text{CuOH}^+)_{2.0}(\text{NH}_4^+)_{10.0}\text{-A}$ , b:  $(\text{CuOH}^+)_{1.24}(\text{NH}_4^+)_{10.76}\text{-A}$ , c:  $(\text{CuOH}^+)_{0.85}(\text{NH}_4^+)_{11.15}\text{-A}$ , and d: zeolite A ( $\text{Na}_{12}\text{-A}$ ).



**Figure 4.** The DSC and TG thermograms of solvated  $(\text{CuOH}^+)_{2}(\text{NH}_4^+)_{10}\text{-A}$  zeolite.

oxygen. In this work, the damage of zeolite framework could be reduced by making the exchanging solution high basic ( $\text{pH} = 12.3$ ) by adding excess ammonia.

The relative high thermal stability of  $(\text{Cu}(\text{NH}_3)_3\text{OH}^+)_x(\text{NH}_4^+)_{12-x}$

-A·zH<sub>2</sub>O ( $x \leq 2.0$ ) zeolite also may be attributable to the formation of hydroxotriammineCu(II) complex ion which will reduce the ions hydrolyzing ability due to the reduced charge and decreased ionic potential ( $\phi = z + /r_+$ ) by the coordination of OH<sup>-</sup> ions and ammonia molecules.

Since the hydrated (Cu(NH<sub>3</sub>)<sub>3</sub>OH<sup>+</sup>)<sub>2</sub>(NH<sub>4</sub><sup>+</sup>)<sub>10</sub>-A·zH<sub>2</sub>O showed a smooth and continuous weight loss due to the dehydration and deammoniation, a considerable overlaps between adjacent peaks are expected in thermogram.

The hydrated (Cu(NH<sub>3</sub>)<sub>3</sub>OH<sup>+</sup>)<sub>2</sub>(NH<sub>4</sub><sup>+</sup>)<sub>10</sub>-A·zH<sub>2</sub>O showed four endothermic DSC peaks around 80°C (shoulder), 140°C, 210°C, and 380°C, respectively. The first peak (80°C) may arise from the dehydration of waters bound weakly to the zeolite surface, and the second one (140°C) may be attributable to the dehydration of water molecules bound more strongly to the cations inside framework. As the temperature is raised above 190°C, the deep blue color of hydroxotriammine Cu(II) complex ion became gradually pale blue. The blue color was lost completely around 240°C and changed to white indicating that hydroxotriammine Cu(II) complex ion have lost all of the coordinated ammonia. About six ammonia molecules (6.4 NH<sub>3</sub>) were detected by the acid-base titration of evolved ammonia in the range of 190°C to 240°C.

So the third DSC peak ( $T_m$ : 210°C) could be attributable to the deammoniation of the hydroxotriammine Cu(II) complex ion. At higher temperature ranging from 240°C to 430°C, about ten ammonia molecules (9.3 NH<sub>3</sub>) were evolved. It has been reported that NH<sub>4</sub><sup>-</sup>-exchanged zeolite X and Y show second endothermic DTA peak above 250°C due to the deammoniation of ammonium ion and that the deammoniation are made more than 90% below 400°C and almost completed at 500°C.<sup>1b</sup> Based on our experiments and previous reports,<sup>1b</sup> the fourth DSC peak ( $T_m$ : 380°C) ranging from 240°C to 430°C could be attributed to the deammoniation of ammonium ions.

The activation energies determined by Ozawa's<sup>24</sup> plot on the above thermal reactions are as follows; dehydration (second peak, around 140°C): 90.82 kJ/mol, deammoniation of hydroxytriammine Cu(II) ion (third peak around 210°C): 99.97 kJ/mol, decomposition of ammonium ion (fourth peak around 380°C): 176.57 kJ/mol.

**Acknowledgement.** The present study was supported in part by the Basic Science Research Institute Program, Ministry of Education, Korea, 1991, Project No. BSRI-91-306.

## References

1. (a) Breck, D. W. *Zeolite Molecular Sieves*; Wiley-Intersci-

- ence: New York, U. S. A. 1974, p 29-94; (b) *ibid.* p 481.
2. Seff, K. *Acc. Chem. Res.* 1976, 9, 121.
3. Lee, H. S.; Cruz, W. V.; Seff, K. *J. Phys. Chem.* 1982, 86, 3562.
4. Kim, Y.; Subramanian, V.; Firror, R. L.; Seff, K. *ACS Symposium Series No. 135, Adsorption and Ion Exchange with Synthetic Zeolites*; American Chemical Society: Washington D. C., U. S. A., 1980; p 137.
5. Park, J. Y. *Bull. Korean Chem. Soc.* 1991, 12, 265.
6. Flanigen, E. M.; Khtami, H.; Szymanski, H. A. *Adv. Chem. Series* 1971, 101, 301.
7. Dutta, P. K.; Barco, B. D. *J. Phys. Chem.* 1989, 89, 1861.
8. Schoonheydt, R. A.; Vaesen, L.; Leeman, H. *J. Phys. Chem.* 1989, 93, 1515.
9. Janssen, R. G.; Tizink, A. H.; Veeman, W. S.; Maesen, Th. L. M.; Van Lent, J. F. *J. Phys. Chem.* 1989, 93, 899.
10. No, K. T.; Bae, D. H.; Jhon, M. S. *J. Phys. Chem.* 1986, 90, 1772.
11. No, K. T.; Kim, J. S.; Huh, Y. Y.; Kim, W. K.; Jhon, M. S. *J. Phys. Chem.* 1987, 91, 740.
12. Akporiaye, D. E.; Price, G. D. *Zeolites* 1989, 9, 321.
13. Mortier, W. J. *J. Phys. Chem.* 1980, 84, 1982.
14. Beran, S. J. *J. Mol. Catal.* 1981, 10, 17.
15. Datka, J.; Greelings, P.; Mortier, W.; Jacobs, P. *J. Phys. Chem.* 1985, 89, 3484.
16. Fletcher, R. *Fortran subroutines for minimization by Quasi-Newton methods*, A. E. R. E. Report, R7125, United Kingdom Atomic Energy Authority Research Group. U. K., 1972, 1-28.
17. Ahmed, N. A.; Kitaigorodskii, A. I. *Acta Cryst.* 1972, B28, 739.
18. Johnson, C. K. *Oak Ridge Thermal-Ellipsoid Plot Program for Crystal Structure (ORTEP)*; Third Revision of ORNL-3794, Oak Ridge National Laboratory, Oak Ridge, Tennessee, U. S. A., 1976.
19. Herman, R. *Inorg. Chem.* 1979, 18, 995.
20. Mcusker, L. B.; Seff, K. *J. Am. Chem. Soc.* 1981, 103, 3441.
21. Park, J. Y.; Kim, Y.; Kim, U. S.; Choi, S. G. *J. Korean Chem. Soc.* 1989, 33, 357.
22. Heo, N. H.; Cruz-Pataiinghug, W.; Seff, K. *J. Phys. Chem.* 1986, 90, 3931.
23. Baes, Jr. C. F.; Mesmer, R. E. *John Wiley & Sons* (1976), *The Hydrolysis of Cations*; John Wiley & Sons: N. Y., U. S. A., p 241-246.
24. Ozawa, T. *J. Therm. Anal.* 1975, 7, 601.